MSR DC ADVANCED

SILYL MODIFIED POLYMER

KEY BENEFITS

- Sandable after curing
- High temperature resistance
- Good UV and weather resistance

PRODUCT DESCRIPTION

Bostik MSR Deck Caulk Advanced is a 1-component, permanently elastic, fast curing sealant specifically developed for deck caulking applications in the yacht and boat building industry.

APPLICATIONS

- Bostik MSR Deck Caulk Advanced is designed for watertight sealing of seams in teak decks and other decking materials.

FEATURES

- Excellent UV-resistance and ageing properties; good resistance against fresh and salt water
- Product can be sanded after curing
- MED Certified by Bureau Veritas: IMO FTP code 2010
- Solvent and isocyanate free
- High chemical resistance

METHOD OF USE

For specific application instructions consult the Bostik instruction brochure “Application manual for bonding & caulking of teak decks”.
Bostik MSR DC Advanced can easily be extruded with a hand or air pressure gun at temperatures between +5°C and +35°C. Bostik MSR DC Advanced should tooled or smoothed within 25 minutes (at 23°C/50% R.H.) of applying MSR DC Advanced.
A minimum adhesive thickness of 2 mm is recommended. In sealing applications, MSR DC Advanced should be tooled or smoothed within 25 minutes (at 23°C/50% R.H.) using a spatula or putty knife, occasionally moistened with a soap solution. Ensure to avoid soap solution penetrating between joint surface and adhesive, as this will cause loss of adhesion.
Cleaning tools or removing uncured residue of MSR DC Advanced can be done with a clean colourless cloth, wetted with Bostik Liquid 1 or Bostik Cleaner E.
Cleaning of Teak Decks:
See separate instruction brochure “Application manual for bonding & caulking of teak decks”. In order to keep the teak decks in optimum shape we recommend cleaning with (salt) water or diluted pH neutral green soap and a soft brush. The brush must be used in a parallel direction to the teak planks. After cleaning the deck should be flushed with abundant fresh or salt water to remove excess soap.
We strictly advise against the use of detergents, cleaners and other chemicals as they may affect the deck caulk. Note that the use of high-pressure cleaning equipment can severely damage the deck and deck caulk.

TECHNICAL DATA

Basic Material		Silyl Modified Polymer (SMP)
Specific Gravity	[g/ml]	ca. 1.4
Skin Forming Time 23°C/50% R.H.	[min]	ca. 25
Curing Mechanism		Moisture
Curing Speed 23°C/50% R.H.	[mm]	ca. 2.5
Shore A Hardness		ca. 48
Color		Black
Tensile Stress At 100%		ca. 1.8
Volume Change	[%]	ca. < 3
Tensile Stress At Break ISO 37 (dumbbells)	[MPa]	ca. 3.0
Elongation At Break ISO 37 (dumbbells	[%]	ca. 200
Shear Stress ISO 4587	[MPa]	ca. 2.1
Temperature Resistance	[°C]	-40 to +110*
Application Temperature	[°C]	+ 5 to +40
UV And Weather Resistance		Excellent

* = 10 Cycles of 7 hours at 110°C followed by 17 hours at 23°C/50%RH.

PACKAGING DESCRIPTION

290ml cartridge
600ml sausage
200l drum

ADHESION

To obtain an excellent bonding on teak wood, a clean, dry and grease-free surface is required. The teak wood should be cleaned with Bostik Cleaner E and allowed to dry for a minimum of 5 minutes.
The deck wood seams should then be pre-treated with Bostik Prep P and allowed to dry for a minimum of 1 hour (max. 6 hours) before application of Bostik MSR DC Advanced.
For optimal use of MSR DC Advanced's high elasticity, a minimum joint dimension relative to the width of the deck is recommended.
For more details on Prep P, consult the concerned Technical Data Sheet.

STORAGE STABILITY


Bostik MSR Deck Caulk Advanced can be stored for 18 months in cartridge and 12 months in sausage, in the original unopened container in a dry place at temperatures between +5°C and +30°C.

FURTHER INFORMATION

- The following publication is available on request: Material Safety Data Sheets (MSDS).

- Certificate GL elastomeric adhesive, class A and B

- This product has been tested and certified to the International Maritime Organisation (IMO) Fire Test Procedures for surface flammability. Not only are the fire retardant properties excellent, but also the production quality is ensured and regularly audited by Bureau Veritas, which guarantees the constant quality Bostik stands for.



DISCLAIMER

Bostik provides this Technical Data Sheet ("TDS") for descriptive and informational purposes only. It does not constitute a warranty, a contract, or a substitute for expert or professional advice. Please refer to the local product Safety Data Sheet for health and safety information. The statements, technical information, data, and recommendations contained in this TDS are provided "AS IS" without any warranties or guarantees of any kind. They represent typical results for the products based solely on Bostik's research. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability for any damages of any kind that may result from the use of the products, the results obtained, or reliance on the information contained herein.

Bostik SA
51, Esplanade du Général de Gaulle,
92800 Puteaux – France
Smart help: +33 149 007 502
www.bostik.com

All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.